

No: 2017D0305

Product	Fiberglass mesh				Report	Mar.14 th ,2017
Name					Date	
Specification	125g/m ² , 10x10mm				Sample	3 m²
					Qty	
No.	ITEM		UNIT	STANDARD	RESULT	CONCLUSION
1	Tensile	Warp	N/50mm	750N	1221	Up to standard
	strength	Weft			1216	
2	Alkali		%	≥50%	56%	Up to standard
	resistance					
3	Content	of	g/m²	≥ 13%	14%	Up to standard
	resin %					
4	Weight	per	g/m²	≥ 115	125	Up to standard
	unit area					

STANDARD BASIS: JG 149-2003

REPORT CONCLUSION: In accordance with industrial standard